

# Cyberbond Cyanacrylat Klebstoff Sekundenkleber



**Cyberbond Europe GmbH**  
Werner-von-Siemens-Str. 2  
D – 31515 Wunstorf  
Germany  
Tel.: + 49 / 5031 / 95 66 – 0  
FAX.: + 49 / 5031 / 95 66 – 26  
E-mail: [info@cyberbond.de](mailto:info@cyberbond.de)  
[www.cyberbond.eu](http://www.cyberbond.eu)  
**Status: 30.06.2010**

## TDS - Technical Data Sheet / Technisches Datenblatt

### CB 2241

#### Profile:

Flexible product, to bond materials with different elongation, **ISO 10993-5** approved

#### Kurzbeschreibung:

Flexibilisiert, für Materialien unterschiedlicher Ausdehnung, **ISO 10993-5** freigegeben

### Physical Properties / Physikalische Eigenschaften

#### Monomer Cyanoacrylate (fluid) / Monomeres Cyanacrylat (flüssig)

- |   |                     |                 |
|---|---------------------|-----------------|
| • Monomer Base / Basis Monomer:   |                     | Ethylester      |
| • Appearance / Aussehen:  |                     | black / schwarz |
| • Viscosity at 20 °C in / Viskosität bei 20 °C in   | mPa·s:              | 2000 - 4000     |
| • Density at 20 °C in / Dichte bei 20 °C in   | g/cm <sup>3</sup> : | 1,06            |
| • Flashpoint / Flammpunkt   | °C:                 | 85              |
| • Shelf life at 20° c in unopened containers in / Lagerstabilität bei 20° c in ungeöffneten Gebinden in | months/<br>Monaten: | 9               |

#### Setting Time on ... / Aushärtegeschwindigkeit an ...

- |   |      |         |
|---|------|---------|
| • Metal (steel) in / Metall (Stahl) in      | sec: | 30 - 90 |
| • Elastomer (EPDM) in / Elastomer (EPDM) in | sec: | 9 - 13  |
| • Plastic (ABS) / Kunststoff (ABS)          | sec: | 7 - 13  |
| • Wood (beech) in / Holz (Buche) in         | sec: | >40     |

#### Polymer Cyanoacrylate (solid) / Polymeres Cyanacrylat (ausgehärtet)

- |   |                     |             |
|---|---------------------|-------------|
| • Tensile strength on rubber (NBR) in / Zugfestigkeit an Gummi (NBR) in | N/cm <sup>2</sup> : | # 82 - 100  |
| • Shear strength on steel in / Zugscherfestigkeit an Stahl in           | N/mm <sup>2</sup> : | 10 - 28     |
| • Temperature range in / Temperatureinsatzbereich in                    | °C:                 | -55 / + 140 |

# = Material failure / Materialbruch    n.r. = not recommended / nicht empfehlenswert

The data mentioned in this TDS, particularly the recommendations for application and use of products are based on our recent knowledge and experience. Due to the fact of having so many different materials involved and conditions of applications which are out of our influence, we strongly recommend to do sufficient tests in order to guarantee that Cyberbond products are suitable for the intended process and applications. Except for wilful acts any liability based on such recommendations or any verbal advice is hereby expressly excluded.

Die in diesem TDS enthaltenen Angaben, im Besonderen die Vorschläge zur Verarbeitung und Verwendung der Cyberbond Produkte, basieren auf unseren neuesten Kenntnissen und Erfahrungen. Da die Materialien aber sehr unterschiedlich sein können, und wir auch keinen Einfluss auf die Arbeitsbedingungen haben, empfehlen wir unbedingt, ausreichende Eigenversuche durchzuführen, um die Eignung der Produkte zu bestätigen. Eine Haftung kann weder aus diesen Hinweisen noch aus der mündlichen Beratung begründet werden, es sei denn, dass uns Vorsatz oder grobe Fahrlässigkeit nachgewiesen werden kann.

## Haftungsausschluss

Unsere anwendungstechnische Beratung in Wort und Schrift und durch Versuche erfolgt nach dem heutigen Stand unserer und unserer Produzenten Kenntnisse. Sie befreit Sie jedoch nicht von der eigenen Prüfung, der von uns gelieferten Produkte, auf deren Eignung für die beabsichtigten Verfahren und Zwecke. Anwendung, Verwendung und Verarbeitung der Produkte erfolgen außerhalb unserer Kontrollmöglichkeiten und liegen daher ausschließlich in Ihrem Verantwortungsbereich. Etwa bestehende Schutzrechte Dritter sind zu berücksichtigen. Unsere Produzenten gewährleisten die einwandfreie Qualität unserer Produkte nach Maßgabe der allgemeinen Verkaufs- und Lieferbedingungen.

All recommendations for use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply. Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information, please consult the corresponding product safety data sheets.